

# MEDIRELEASE® 2815

## Paper and Film Release Liners

### Description

Polymer release coated substrate. Suitable for use as a medical release carrier/delivery film in high temperature film applications.

### Characteristics

- Offers consistent, stable release
- Provides a carrier for films used in differential release applications
- Can be used in coating or extrusion processes as a carrier
- Low moisture absorption

### Properties

#### Tests Performed

#### Typical Values

Caliper (mils)	5.0
Bond (g/2 inch)	>300 g/2 inch
Basis weight (g/m <sup>2</sup> )	105 g/m <sup>2</sup>

Typical values are intended to be used as a guide and are not intended for specification purposes

### Construction

- ← Polymer release coating
- ← Paper



### Ordering Information

Width	Maximum 62 inches
Diameter	Maximum 26 inches
Length	Maximum ~7,000 feet
Safety Testing	Consistent with intended application
Storage	Temperature 50-80°F; Humidity 40-60%

### Limited Warranty and Conditions—Please Read Carefully

Mylan believes the information in this publication is an accurate description of the typical; characteristics and/or uses of the product(s). It is the purchaser's responsibility to thoroughly test the product in the purchaser's specific application to determine its performance, efficacy and safety, especially in light of any third party intellectual property rights. Suggestions of uses should not be taken as inducements to infringe any particular patent or other protected proprietary rights.

Unless Mylan provides you with a separate specific written warranty of fitness for a particular use, Mylan's sole warranty is that the product(s) as supplied, will meet Mylan's then current sales specification. MYLAN SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND OF FITNESS FOR USE. Your exclusive remedy and Mylan's sole liability for breach of warranty is limited to refund of the purchase price or replacement of any Mylan product shown to be other than as warranted, and Mylan expressly disclaims any liability for incidental or consequential damages.

Applicable test methods and product specifications